

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 747 521 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
03.03.2004 Bulletin 2004/10

(51) Int Cl.7: **D04H 1/54, D04H 3/14**

(21) Application number: **96304104.1**

(22) Date of filing: **05.06.1996**

(54) **Continuous fiber nonwoven and method for producing the same**

Endlosfaservliesstoff und Verfahren zur Herstellung

Non-tissé de fibres continues et procédé pour sa production

(84) Designated Contracting States:  
**DE GB IT**

(30) Priority: **06.06.1995 JP 16474995**

(43) Date of publication of application:  
**11.12.1996 Bulletin 1996/50**

(73) Proprietor: **CHISSO CORPORATION**  
**Osaka-shi Osaka 530-6591 (JP)**

(72) Inventor: **Terakawa, Taiju**  
**Yasu-gun, Shiga-ken (JP)**

(74) Representative: **W.P. THOMPSON & CO.**  
**Eastcheap House**  
**Central Approach**  
**Letchworth Garden City,**  
**Hertfordshire SG6 3DS (GB)**

(56) References cited:  
**EP-A- 0 391 260** **US-A- 4 269 888**

**EP 0 747 521 B1**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

## Description

[0001] The present invention relates to a continuous fiber nonwoven produced by heat fusion and having excellent bulkiness and high tensile strength. More particularly, the invention provides a continuous fiber nonwoven usable for sanitary materials, engineering materials, agricultural materials, packing materials and the like.

[0002] In methods for producing nonwovens utilizing characteristics of heat fusion, there is known a heat treating method of carding webs comprising staple fibers and also a heat treating method of continuous fiber webs. Although the latter method has the advantage that the production process is simple, the resulting nonwoven has the disadvantages of low flexibility and low bulkiness.

[0003] Conventional continuous fiber nonwovens, which are produced by a method of heat fusion and are usable for sanitary materials, engineering materials and the like, are mainly made of fibers of one component. Since such fibers do not develop crimps, they have low bulkiness.

[0004] Known methods for developing the steric crimps of a spiral form (abbreviated as spiral crimps hereinafter) in the fibers of one component, include a method for developing the spiral crimps based on the difference of heat shrinkage inside the fiber by pulling out the spun fiber while partial quenching is applied to the fiber (Japanese Patent Publication No. 45-1649), and a method for developing the crimps based on the difference of the degree of crystallization by blending a nucleating agent into a certain part of the fiber cross-section (Japanese Patent Application Laid-open No. 5-209354). In the former method, however, the crimps are loosened through the heat treatment process for processing the fiber into a nonwoven and the bulkiness becomes insufficient. In both methods, since the fiber is constituted from one component, a hot pressing method is only used as the heat treatment process for processing the fiber to the nonwoven, so that the spiral crimps of the fiber are pressed, resulting in undesirable bulkiness.

[0005] It is known that spiral crimps can be developed in the fiber by compositely spinning several thermoplastic resins into a parallel or eccentric sheath core type arrangement (Japanese Patent Applications Laid-open Nos. 48-1471 and 63-282350). In the nonwovens using these composite fibers, however, although it is recognized that the bulkiness is improved, the tensile strength is the same as (or less than) that of conventional nonwovens made of one component fiber, so that more improvement has been sought.

[0006] US 4269888 discloses heat-adhesive side-by-side type composite fibers containing a crystalline polypropylene component and an olefin component having few natural crimps and low latent crimpability.

[0007] EP-A-0391260 discloses heat-adhesive composite fibers of two or more thermoplastic resins which may be treated with an air current to form a nonwoven.

[0008] According to one embodiment of the present invention, there is provided a continuous fiber non-woven comprising composite continuous fibers having spiral crimps, the composite continuous fibers comprising compositely spun first and second thermoplastic resins in a composite ratio of 60/40 to 40/60, the second thermoplastic resin having a melting point at least 15°C less than that of the first thermoplastic resin, and an elastic shrinkage at least 1% less than that of the first thermoplastic resin, adjacent fibers of the non-woven being connected together by fused contact points of the second thermoplastic resin on the outside of the spiral crimps.

[0009] According to another embodiment of the present invention, there is provided a continuous fiber non-woven comprising composite continuous fibers having spiral crimps, the composite continuous fibers comprising compositely spun first and second thermoplastic resins in a composite ratio of 60/40 to 40/60, the second thermoplastic resin having a melting point at least 15°C less than that of the first thermoplastic resin, and an elastic shrinkage at least 1% less than that of the first thermoplastic resin, adjacent fibres of the non-woven being connected together by fused contact points of the second thermoplastic resin on the inside of the spiral crimps.

[0010] Preferably, the composite continuous fibers are of a parallel or eccentric sheaf core types.

[0011] According to a further embodiment of the present invention, there is provided a method for producing a continuous fiber non-woven comprising the steps of compositely spinning a first thermoplastic resin and a second thermoplastic resin in a composite ratio of 60/40 to 40/60 into a composite continuous fiber, the second thermoplastic resin having a melting point at least 15°C less than that of the first thermoplastic resin, and an elastic shrinkage at least 1% less than that of the first thermoplastic resin, stretching the composite continuous fiber by at least 1.2 times the length of the unstretched fiber at a temperature lower than the melting point of the second thermoplastic resin to form spiral crimps; and heat treating the composite continuous fiber at a temperature higher than the melting point of the second thermoplastic resin whereby adjacent fibers are connected together by fused contact points of the second thermoplastic resin on the outside of the spiral crimps.

[0012] Preferably, the composite continuous fiber is heat treated at a temperature lower than the softening point of the first thermoplastic resin.

[0013] Conveniently, the composite continuous fiber is heat treated at a temperature higher than the softening point of the first thermoplastic resin whereby the spiral crimps are reversely turned.

[0014] Advantageously, the first thermoplastic resin is crystalline polypropylene and the second thermoplastic resin is high density polyethylene.

[0015] Preferably, the heat treatment is conducted by a system of an oven with internal air circulation.

[0016] Conveniently, the heat treatment is conducted by a hot pressing system.

[0017] The present invention provides a continuous fiber nonwoven having excellent bulkiness and high tensile strength in view of the above conditions of the continuous fiber nonwovens produced by heat fusion methods.

[0018] The present invention seeks to solve the aforesaid problems by aiming at the relationship between the spiral crimps developed in the composite fibers and the arrangement of components on the fiber cross-section. These aims may be attained by using composite fibers comprising several thermoplastic resins arranged in a parallel or eccentric sheath core type, in which the thermoplastic resin having a lower melting point is located on the outside of the spiral crimps developed by stretching the fibers.

[0019] There is disclosed herein a continuous fiber nonwoven comprising composite continuous fibers having spiral crimps obtained by compositely spinning two thermoplastic resins having a difference in melting point of 15°C or more, characterised in that the contact points of the fibers are adhered to one another by fusing of the thermoplastic resin having the lower melting point and located on the outside of the spiral crimps.

[0020] There is also disclosed herein a method for producing a continuous fiber nonwoven comprising: preparing a first thermoplastic resin and a second thermoplastic resin having a melting point at least 15°C less than that of the first thermoplastic resin and an elastic shrinkage 1% less than that of the first thermoplastic resin; compositely spinning these resins in a composite ratio of 60/40 40/60 into a parallel type or an eccentric sheath core type, in which the second thermoplastic resin is a sheath and the first thermoplastic resin is a core eccentric to the sheath; stretching the resulting yarn over 1.2 times as long as the unstretched yarn at a temperature lower than the melting point of the second thermoplastic resin; and heat treating the yarn at a temperature higher than the melting point of the second thermoplastic resin and lower than the softening point of the first thermoplastic resin to adhere one to the other at the contact points of the fibers.

[0021] The thermoplastic resins used as raw materials of composite continuous fibers can include, for example, polyolefins such as polypropylene, polyethylene, ethylenepropylene copolymer, propylene-butene-1 copolymer, ethylene-propylene-butene-1 copolymer, ethylene-vinyl acetate copolymer, and poly-4-methylpentene-1, polyolefins modified with unsaturated carboxylic acids or their anhydride, polyesters such as polyethylene terephthalate, polyethylene terephthalate-isophthalate copolymer and polybutylene terephthalate, polyamides such as nylon 6, nylon 66 and nylon 12, thermoplastic polyurethane and the like.

[0022] In the present invention, a combination of two kinds of thermoplastic resins having a difference in melting point of 15°C or more is selectively used. In this case, it is necessary to use spinning conditions so that the elastic shrinkage of the thermoplastic resin having a higher melting point becomes 1% or more higher than that of the thermoplastic resin having a lower melting point.

[0023] With the present invention, nonwovens are obtained by heat treating the composite continuous fibers and adhering the contact points of fibers by fusing only thermoplastic resin having a lower melting point. If the difference of the melting points of two thermoplastic resins, which are raw materials of composite fibers, is less than 15°C, this is undesirable because the temperature range usable in the heat treatment becomes narrow.

[0024] The term "elastic shrinkage" means a shrinkage that unstretched yarn of one component is stretched to the same draw ratio (K) as drawing conditions of the composite fibers and at once the load is removed, and the following equation is provided.

$$\text{Elastic shrinkage } S(\%) = 100 \times (KA-B)/(KA-A)$$

A: length of unstretched yarn

B: length of yarn at removal of load after stretching the yarn.

[0025] When it is impossible to spin one component fiber of thermoplastic resin (a), or it is impossible to stretch it to the length of 1.5 times, elastic shrinkage (S1) of the unstretched yarn composed of a single component of thermoplastic resin (b) having excellent stretch properties, and elastic shrinkage (Sc) of the unstretched yarn composite fibers composed of thermoplastic resin (a) and thermoplastic resin (b), are measured; and the elastic shrinkage (S2) of the unstretched yarn of thermoplastic resin (a) is calculated by the following equation:

$$S2 = 2Sc - S1$$

[0026] When the difference of the elastic shrinkages of two thermoplastic resins is less than 1%, distinct crimps are not observed after stretching the composite fibers, and one cannot obtain sufficiently bulky nonwovens. In the case of two thermoplastic resins, if the elastic shrinkage of the thermoplastic having a higher melting point is less than that of

the thermoplastic resin having a lower melting point, it is impossible to locate the thermoplastic resin having a lower melting point on the outside of the spiral crimps which appear after the composite fibers are stretched.

**[0027]** In the composite continuous fibers used in the present invention, two thermoplastic resins selected in accordance with the above standards are preferably compositely spun into a parallel type or an eccentric sheath core type in the range of a composite ratio of 60/40 - 40/60. Since the crimps of the composite fibers are based on the difference between the elastic shrinkages of both components, clear crimps do not appear when one component is present at less than 40%, so that sufficiently bulky nonwovens are not obtainable. In case of the eccentric sheath core type, thermoplastic having the lower melting point is used at the sheath side of the composite fibers.

**[0028]** Crystalline polypropylene/polyethylene can be exemplified as a desirable combination of two thermoplastic resins, and crystalline polypropylene having a wide molecular weight distribution can desirably be used as a thermoplastic resin having a high melting point, because it shows a relatively high elastic shrinkage.

**[0029]** After the unstretched yarn obtained by the composite spinning is stretched, and immediately the stress is removed, the spiral crimps develop in the composite fibers. The curvature radius of the spiral is based not only on physical properties of the differences between the elastic shrinkages of the raw material resins, the Young's modulus, the fineness and the like, but also on the stretching temperature and the draw ratio. The stretching conditions are selected in accordance with the degree of bulkiness of desired nonwovens (commonly 1.2 - 4 times the length of unstretched yarn, between room temperature and a temperature lower than the melting point of the second thermoplastic resin).

**[0030]** In such obtained composite continuous fibers, the thermoplastic resin having a lower melting point is located on the outside of the spiral crimps.

**[0031]** To obtain the web of the composite continuous fibers having spiral crimps and used in the present invention, two thermoplastic resins selected in accordance with the said standards are compositely spun at the fixed composite ratio, and the unstretched yarn stored on bobbins or in canes is stretched under the fixed stretching conditions and is immediately accumulated on a conveyor. It is also possible to use a spunbond method in which the spun composite fibers are pulled by a stretch machine equipping a feed roll and a draw roll via a quenching device, and then accumulated on a conveyor net in which the fibers are sucked with an air sucker and the fibers are opened.

**[0032]** The continuous fiber nonwoven of the present invention can be obtained by heat treatment of the above composite continuous fiber webs having spiral crimps at a temperature higher than the melting point of the thermoplastic resin having the lower melting point and lower than the softening point of the thermoplastic resin having a higher melting point. In the heat treatment, a hot pressing device such as an embossing roll, or a suction dryer with internal air circulation, or a heater such as an infrared heating oven, may be used.

**[0033]** Although the contact points of the fibers are adhered by heat treatment to fuse the thermoplastic resin having a lower melting point, because the thermoplastic resin having a lower melting point is located on the outside of the spiral crimps in the composite continuous fibers used in the present invention, the fibers contact one another by the thermoplastic resin having a lower melting point, the fibers are adhered to one another by fusion of the same kinds of thermoplastic resins, and nonwovens having a high tensile strength are obtained.

**[0034]** When a hot pressing device is used in the heat treatment, the temperature of the heat treatment may be a temperature near to but above the softening point of the thermoplastic resin having a lower melting point, which is located on the outside of the spiral crimps, so that the thermoplastic resin having a higher melting point does not soften or change the shape by heat, and bulky and soft nonwovens can be obtained.

**[0035]** To obtain nonwovens having a sufficient strength by using the composite fibers in which thermoplastic resin having a lower melting point is located on the inside of the spiral crimps, it is necessary to treat the fibers at higher temperature to soften the thermoplastic resin having a higher melting point, so that the touch of the nonwoven becomes hard.

**[0036]** Since the suction dryer with internal air circulation can provide a sufficient heat capacity without pressing its continuous fiber web, it is preferably used for producing bulky nonwovens at a high speed. In this case, since the thermoplastic resin having a lower melting point is located on the outside of the spiral crimps, the composite fibers contact one another with the thermoplastic resin having a lower melting point to fix the fibers by fusing the same kind of thermoplastic resins, and nonwovens having a high tensile strength are obtained.

**[0037]** When the fibers are heated at a temperature to fuse the thermoplastic resin having a lower melting point, the thermoplastic resin having a higher melting point slightly shrinks to reduce the strain produced by stretching the fibers, while the thermoplastic resin having a lower melting point greatly shrinks and fuses, and as a result, the spiral crimps reversely turn so as to arrange the thermoplastic resin having a high melting point outside the spiral crimps of the composite fibers. By such fibers, the numbers of contact and adhered points among the fibers are increased, thereby to obtain nonwovens having a high strength. Further, since the fibers pull one another between the adhered points, the bulkiness is little decreased.

**[0038]** When the composite fibers, in which the thermoplastic resin having a lower melting point is arranged on the inside of the spiral crimps, are heat treated with a suction dryer, the spiral crimps of the composite fibers become

smaller by the shrinkage and the fusing of the thermoplastic resin having a lower melting point, the bulkiness of the nonwoven is lost, and the strength of the nonwoven decreases with the decrease in number of the adhered points among the thermoplastic resins having a lower melting point.

[0039] Since the continuous fiber nonwoven of the present invention is obtained by using the composite continuous fibers as raw fiber materials in which the thermoplastic resin having a lower melting point is located on the outside of the spiral crimps, it has the same or a higher degree of tensile strength in comparison with conventional nonwovens of continuous fibers, and it has high bulkiness which is not observed in the conventional nonwovens. Accordingly, it is possible to use the nonwovens of the present invention as sanitary materials for surface materials of diapers and the like, geotextile materials, packaging materials, etc.

[0040] The present invention is illustrated more specifically by the following Examples and comparative Examples. The physical values in these Examples are determined by the following methods.

#### Elastic shrinkage:

[0041] An unstretched yarn of one component fibers and an unstretched yarn of composite fibers are stretched at a grip distance of 10 cm and a stretching rate of 10 cm/min to the same magnification (K) in Examples and comparative Examples, and these yarns are immediately returned to the beginning grip distance, the fiber length (c) of a zero point of the stretching load is measured and then the elastic shrinkage (S) is calculated by the following equation:

$$\text{Elastic shrinkage } S (\%) = 100 \times (10K - c) / (10K - 10)$$

$$S2 = 2Sc - S1$$

#### Arrangement of components of spiral crimps:

[0042] A specimen having one cycle length of the spiral crimps is cut off from the composite fibers, it is put between two pieces of cover glass to form a circle, and observing the melting behavior of the thermoplastic resin having a lower melting point by using an optical microscope equipping a hot stage, the arrangement of components is identified.

#### Number of crimps:

[0043] A fiber having ten spiral crimps is cut off and the straight length L (cm) is measured and the number of crimps is calculated using the following equation:

$$\text{Number of crimps (crimps/inch)} = 10 \times 2.54 / L$$

#### Specific volume of nonwoven:

[0044] Four test pieces having 10 cm length and 10 cm width are piled, a plate having the same length and width and 20 g weight is put on the test pieces, the thickness D (cm) of the four test pieces is measured, the total weight W1 (g) of the four test pieces is previously measured, and the specific volume of nonwoven is calculated by the following equation:

$$\text{Specific volume of nonwoven (cm}^3/\text{g)} = 100 \times D / W1$$

#### Tensile strength of nonwoven:

[0045] Test pieces having 20 cm length and 5 cm width (weight is W2) are cut off from nonwoven in a machine direction of nonwoven production (MD) and its cross direction (CD), maximum load power P (g) is measured at a grip distance of 10 cm and a stretching rate of 10 cm/min, and the tensile strength is calculated using the following equation after  $\text{gr/m}^2$  is corrected:

$$\text{Tensile strength (g/(cm} \times \text{g/m}^2)) = P / 500W2$$

## EP 0 747 521 B1

$$\text{Geometric mean strength} = (\text{MD strength} \times \text{CD strength})^{1/2}$$

Examples 1 to 5 and comparative Examples 1 to 4:

5

**[0046]** Table 1 shows the production conditions of raw continuous fibers and properties of the continuous fibers used for nonwovens of the Examples and the comparative Examples.

10

15

20

25

30

35

40

45

50

55

(Table 1)

	Spinning and stretching conditions										Properties of fibers			
	Fiber components Type	Temp. of extruder °C	Spinner-let temp. °C	Elastic shrinkage %	Difference of elastic shrinkage%	Fineness d	Stretch temp. °C	Stretch ratio	Arrangement outside/inside	Number of crimps	Yarn strength g/d	Yarn elongation %		
Example 1	HDPE Parallel PP1	240 290	280	25.2 27.8	2.6	2.0	room temp.	2.0	HDPE PP1	6.5	2.43	169		
Example 2	HDPE Parallel PP2	240 290	280	25.2 32.2	7.0	2.0	room temp.	2.0	HDPE PP2	12.0	2.25	180		
Example 3	HDPE eccentric sheath core PP2	240 310	280	25.2 32.2	7.0	2.0	room temp.	2.0	HDPE PP2	9.5	2.12	195		
Example 4	HDPE eccentric sheath core PP2	240 310	280	27.5 36.7	9.2	2.0	room temp.	1.7	HDPE PP2	11.0	1.88	224		
Comparative example 1	PP1 only one	290	260	27.8	---	2.0	room temp.	2.0	---	0	2.71	136		
Comparative example 2	HDPE Parallel PP2	240 290	280	25.2 26.0	0.8	2.0	---	---	PP1 HDPE	7.8	1.38	275		
Comparative example 3	HDPE Parallel PP2	240 340	280	25.2 26.0	0.8	2.0	room temp.	2.0	Developing poor crimps	2.0	1.98	206		

Note: PP1 = Crystalline polypropylene, MFR=10, 0-3.5, m.p.=164°C, s.p.=144°C

PP3 = Crystalline polypropylene, MFR=25, 0-5.0, m.p.=164°C, s.p.=143°C

HDPE = High-density polyethylene, MFR=40, m.p.=129°C, s.p.=100°C

[0047] Fibers of Examples 1 to 3, which were obtained by combining crystalline polypropylene and high-density polyethylene, compositely spinning them, and stretching the yarn, have developed desirable spiral crimps by arranging 5 high-density polyethylene outside the spiral crimps. In Example 2, composite fiber having many crimps is obtained by the same conditions of spinning and stretching as in Example 1. It is considered that the fact is caused by using

5 crystalline polypropylene having wide molecular 10 weight distribution (high Q value).  
[0048] Although the composite fiber, which was obtained in Example 3 by using the same raw materials, spinning temperature and stretch conditions as in Example 2, develops desirable spiral crimps arranging high-density polyethylene, the number of crimps is less by changing the composite type to an eccentric sheath core type. However, by changing the stretch conditions, it was possible to obtain the composite fiber of the eccentric sheath core type having

10 many crimps (Example 4).  
[0049] The fiber comprising one component of crystalline polypropylene (comparative Example 1) does not develop the spiral crimps even though the fiber was stretched as in Example 1.

[0050] In comparative Example 2, in which the fiber was extruded by using the same conditions as in Example 1 and directly spun with an air-sucker instead of machine stretching, the fiber developed spiral crimps, on the inside of which

15 high-density polyethylene, the component having a low melting point, was arranged.  
[0051] In comparative Example 3, in which the composite fiber was obtained by spinning and stretching the yarn by the same process as in Example 1 except that the extrusion temperature of crystalline polypropylene was increased, the difference of elastic shrinkages became smaller and very poor spiral crimps were developed.

20 [0052] The webs of various continuous fibers were processed by heat treatment with a heat oven with internal air circulation or a heat embossing roll to obtain nonwovens. The process conditions and the physical properties of the nonwovens are shown in Table 2.



(Table 2)

	Processing conditions		Physical properties of nonwoven			
	Air circulation oven temperature Treating time	Emboss. temp. Emboss. area	Basis weight g/m <sup>2</sup>	Thickness mm	Specific volume cm <sup>3</sup> /g	Geometric mean strength (*)
Example 1	135°C 1.7 sec.	-- --	30	1.19	39.8	26.3
Example 2-1	135°C 1.7 sec.	-- --	30	1.46	48.8	26.0
Example 2-2	-- --	125°C 15%	30	0.70	23.3	28.0
Example 3	135°C 1.7 sec.	-- --	30	1.37	45.6	27.3
Example 4	135°C 1.7 sec.	-- --	30	1.40	46.5	24.8
Comparative example 1	-- --	145°C 15%	31	0.26	8.5	30.0
Comparative example 2-1	135°C 1.7 sec.	-- --	31	0.94	30.3	12.2
Comparative example 2-2	-- --	125°C 15%	30	0.51	17.0	15.5
Comparative example 3	135°C 1.7 sec.	-- --	30	0.46	15.2	25.4

(\*) : g/(cm · g/m<sup>2</sup>)

[0053] The nonwoven comprising one component fiber of crystalline polypropylene obtained in comparative Example 1 is poorer in bulkiness and strength than those of the other Examples.

[0054] The nonwoven prepared in comparative Example 2-1 by using the same raw materials and process conditions

as in Example 1 is poor in bulkiness (thickness and specific volume) and strength in comparison with the nonwoven in Example 1. It is considered that the fact is caused by arranging crystalline polypropylene having elastic shrinkage outside of the spiral crimps, and by arranging high-density polyethylene having adhesion properties on the inside of the spiral crimps.

**[0055]** The nonwoven prepared by a heat embossing roll in Example 2-2 is poor in bulkiness, but it is good in strength in comparison with the nonwoven obtained in Example 2-1. The nonwoven of Example 2-2 is good in both bulkiness and strength in comparison with the nonwoven prepared by the heat embossing roll in comparative Example 2-2.

**[0056]** Although the raw materials are different from those in Example 1, the nonwovens of Examples 3 and 4, in which the difference of the elastic shrinkage and the constitution of the spiral crimps satisfy the requirements of the present invention, show better properties than those of the nonwoven of Example 1. Compared with the nonwovens of Examples, the nonwoven of comparative Example 3, which does not satisfy the above requirements of the present invention, is poor in both bulkiness and strength.

## Claims

1. A continuous fiber non-woven comprising composite continuous fibers having spiral crimps, the composite continuous fibers comprising compositely spun first and second thermoplastic resins in a composite ratio of 60/40 to 40/60, the second thermoplastic resin having a melting point at least 15°C less than that of the first thermoplastic resin, **characterized in that** the second thermoplastic resin has an elastic shrinkage at least 1% less than that of the first thermoplastic resin, adjacent fibers of the non-woven being connected together by fused contact points of the second thermoplastic resin on the outside of the spiral crimps.
2. A continuous fiber non-woven comprising composite continuous fibers having spiral crimps, the composite continuous fibers comprising compositely spun first and second thermoplastic resins in a composite ratio of 60/40 to 40/60, the second thermoplastic resin having a melting point at least 15°C less than that of the first thermoplastic resin, **characterized in that** the second thermoplastic resin has an elastic shrinkage at least 1% less than that of the first thermoplastic resin, adjacent fibres of the non-woven being connected together by fused contact points of the second thermoplastic resin on the inside of the spiral crimps.
3. A continuous fiber non-woven according to claim 1 or claim 2 wherein the composite continuous fibers are of a parallel or eccentric sheaf core types.
4. A method for producing a continuous fiber non-woven comprising the steps of compositely spinning a first thermoplastic resin and a second thermoplastic resin in a composite ratio of 60/40 to 40/60 into a composite continuous fiber, the second thermoplastic resin having a melting point at least 15°C less than that of the first thermoplastic resin, of stretching the composite continuous fiber by at least 1.2 times the length of the unstretched fiber at a temperature lower than the melting point of the second thermoplastic resin to form spiral crimps, **characterized in that** the second thermoplastic resin has an elastic shrinkage at least 1% less than that of the first thermoplastic resin, and **characterized by** heat treating the composite continuous fiber at a temperature higher than the melting point of the second thermoplastic resin whereby adjacent fibers are connected together by fused contact points of the second thermoplastic resin on the outside of the spiral crimps.
5. A method according to claim 4, wherein the composite continuous fiber is heat treated at a temperature lower than the softening point of the first thermoplastic resin.
6. A method according to claim 4, wherein the composite continuous fiber is heat treated at a temperature higher than the softening point of the first thermoplastic resin whereby the spiral crimps are reversely turned.
7. A method according to claim 4 or 5, wherein the first thermoplastic resin is crystalline polypropylene and the second thermoplastic resin is high density polyethylene.
8. A method according to any one of claims 4 to 6, wherein the heat treatment is conducted by a system of an oven with internal air circulation.
9. A method according to any one of claims 3 to 6, wherein the heat treatment is conducted by a hot pressing system.

## Patentansprüche

1. Endlosfaser-Vliesstoff, umfassend Endlos-Kompositfasern mit spiraler Kräuselung, wobei die Endlos-Kompositfasern ein kompositmäßig gesponnenes erstes und zweites thermoplastisches Harz in einem Kompositverhältnis von 60/40 bis 40/60 umfassen, wobei das zweite thermoplastische Harz einen Schmelzpunkt von wenigstens 15°C unter dem des ersten thermoplastischen Harzes hat,  
**dadurch gekennzeichnet, dass** das zweite thermoplastische Harz eine elastische Schrumpfung von wenigstens 1 % weniger als die des ersten thermoplastischen Harzes aufweist und wobei benachbarte Fasern des Vliesstoffes durch verschmolzene Kontaktpunkte des zweiten thermoplastischen Harzes an der Außenseite der Spiralkräuselung miteinander verbunden sind.
2. Endlosfaser-Vliesstoff, umfassend Endlos-Kompositfasern mit spiraler Kräuselung, wobei die Endlos-Kompositfasern ein kompositmäßig gesponnenes erstes und zweites thermoplastisches Harz in einem Kompositverhältnis von 60/40 bis 40/60 umfassen, wobei das zweite thermoplastische Harz einen Schmelzpunkt von wenigstens 15°C unter dem des ersten thermoplastischen Harzes hat,  
**dadurch gekennzeichnet, dass** das zweite thermoplastische Harz eine elastische Schrumpfung von wenigstens 1 % weniger als die des ersten thermoplastischen Harzes aufweist und wobei benachbarte Fasern des Vliesstoffes durch verschmolzene Kontaktpunkte des zweiten thermoplastischen Harzes an der Innenseite der Spiralkräuselung miteinander verbunden sind.
3. Endlosfaser-Vliesstoff nach Anspruch 1 oder 2,  
**dadurch gekennzeichnet, dass** die Endlos-Kompositfasern parallele oder außermittige Bündelkerne aufweisen.
4. Verfahren zur Herstellung eines Endlosfaser-Vliesstoffes, umfassend die Schritte  
kompositmäßiges Verspinnen eines ersten thermoplastischen Harzes und eines zweiten thermoplastischen Harzes in einem Kompositverhältnis von 60/40 bis 40/60 zu einer Endlos-Kompositfaser, wobei das zweite thermoplastische Harz einen Schmelzpunkt von wenigstens 15°C unter dem des ersten thermoplastischen Harzes hat, Strecken der Endlos-Kompositfaser auf wenigstens das 1,2-fache der Länge der ungestreckten Faser bei einer Temperatur, die niedriger als der Schmelzpunkt des zweiten thermoplastischen Harzes ist, um eine spirale Kräuselung zu erzielen,  
**dadurch gekennzeichnet, dass**  
das zweite thermoplastische Harz eine elastische Schrumpfung von wenigstens 1 % weniger als die des ersten thermoplastischen Harzes aufweist und **dadurch gekennzeichnet, dass**  
die Wärmebehandlung der Endlos-Kompositfaser bei einer Temperatur höher als der Schmelzpunkt des zweiten thermoplastischen Harzes durchgeführt wird, wobei benachbarte Fasern durch verschmolzene Kontaktpunkte des zweiten thermoplastischen Harzes an der Außenseite der Spiralkräuselung verbunden sind.
5. Verfahren nach Anspruch 4, **dadurch gekennzeichnet, dass**  
die Endlos-Kompositfaser bei einer Temperatur niedriger als der Erweichungspunkt des ersten thermoplastischen Harzes wärmebehandelt wird.
6. Verfahren nach Anspruch 4, **dadurch gekennzeichnet, dass** die Endlos-Kompositfaser bei einer Temperatur höher als der Erweichungspunkt des ersten thermoplastischen Harzes wärmebehandelt wird, wodurch die Spiralverkräuselungen umgekehrt verdreht werden.
7. Verfahren nach Anspruch 4 oder 5, **dadurch gekennzeichnet, dass** das erste thermoplastische Harz ein kristallines Polypropylen ist und das zweite thermoplastische Harz ein Niederdruck-Polyethylen ist.
8. Verfahren nach einem der Ansprüche 4 bis 6, **dadurch gekennzeichnet, dass** die Wärmebehandlung durch ein System eines Ofens mit Innenluftumwälzung durchgeführt wird.
9. Verfahren nach einem der Ansprüche 3 bis 6, **dadurch gekennzeichnet, dass** die Wärmebehandlung durch ein Heißpreßsystem durchgeführt wird.

## Revendications

1. Textile non tissé à fibres continues comprenant des fibres continues composites ayant des frises en spirale, les

fibres composites continues comprenant une première et une seconde résines thermoplastiques filées de manière composite en un rapport de 60 / 40 à 40 / 60, la seconde résine thermoplastique ayant un point de fusion inférieur d'au moins 15 °C à celui de la première résine thermoplastique, **caractérisé en ce que** la seconde résine thermoplastique a un rétrécissement élastique inférieur d'au moins 1 % à celui de la première résine thermoplastique, les fibres adjacentes du textile non tissé étant reliées ensembles par des points de contact fondus de la seconde résine thermoplastique à l'extérieur des frises en spirale.

2. Textile non tissé à fibres continues comprenant des fibres continues composites ayant des frises en spirale, les fibres composites continues comprenant une première et une seconde résines thermoplastiques filées de manière composite en un rapport de 60 / 40 à 40 / 60, la seconde résine thermoplastique ayant un point de fusion inférieur d'au moins 15 °C à celui de la première résine thermoplastique, **caractérisé en ce que** la seconde résine thermoplastique a un rétrécissement élastique inférieur d'au moins 1 % à celui de la première résine thermoplastique, les fibres adjacentes du textile non tissé étant reliées ensembles par des points de contact fondus de la seconde résine thermoplastique à l'intérieur des frises en spirale.

3. Textile non tissé à fibres continues selon la revendication 1 ou la revendication 2, dans lequel les fibres composites continues sont de types d'âme en gerbe parallèle ou excentrique.

4. Procédé de production d'un textile non tissé à fibres continues comprenant les étapes consistant à filer de manière composite une première résine thermoplastique et une seconde résine thermoplastique en un rapport composite de 60 / 40 à 40 / 60 en une fibre composite continue, la seconde résine thermoplastique ayant un point de fusion inférieur d'au moins 15 °C à celui de la première résine thermoplastique, à étirer la fibre composite continue d'au moins 1,2 fois la longueur de la fibre non étirée à une température inférieure au point de fusion de la seconde résine thermoplastique pour former des frises en spirale, **caractérisé en ce que** la seconde résine thermoplastique a un rétrécissement élastique inférieur d'au moins 1 % à celui de la première résine thermoplastique, et **caractérisé par** le traitement thermique de la fibre composite continue à une température supérieure au point de fusion de la seconde résine thermoplastique, moyennant quoi les fibres adjacentes sont reliées ensembles par des points de contact fondus de la seconde résine thermoplastique à l'extérieur des frises en spirale.

5. Procédé selon la revendication 4, dans lequel la fibre composite continue est traitée thermiquement à une température inférieure au point d'amollissement de la première résine thermoplastique.

6. Procédé selon la revendication 4, dans lequel la fibre composite continue est traitée thermiquement à une température supérieure au point d'amollissement de la première résine thermoplastique, moyennant quoi les frises en spirale sont tournées à l'envers.

7. Procédé selon la revendication 4 ou 5, dans lequel la première résine thermoplastique est du polypropylène cristallin et la seconde résine thermoplastique est du polyéthylène haute densité.

8. Procédé selon l'une quelconque des revendications 4 à 6, dans lequel le traitement thermique est effectué par un système d'un four avec circulation d'air interne.

9. Procédé selon l'une quelconque des revendications 3 à 6, dans lequel le traitement thermique est effectué par un système de pressage à chaud.